



# FLOORING GRADE LAMINATES

## TECHNICAL SPECIFICATION

Sr No	Properties	Unit	Requirement as per EN438:2005	Alfaica Conforms
1	Thickness	1 mm	(± 0.10 mm)	√
2	Length / Width	2440 x 1220 mm 3050 x 1300 mm	(± 10, - 0 mm) (± 10, - 0 mm)	√ √
3	Appearance		Should be free from foreign particles	YES
4	Density	gm / cm <sup>3</sup>	1.41	1.45
5	Dimensional stability	% Max – “L” % Max – “T”	0.55 (max) 1.05 (max)	√ √
6	Resistance to dry heat @ 180°C	Grade	4	>4
7	Boiling water Resistance	Mass Increase % (max) Thickness Increase % (max)	10 11.8	8 9
8	Resistance to Steam	Grade	4	>4
9	Resistance to Cigarette Burn	Grade	3	>3
10	Resistance to Ball impact	NEMA LD3 (3.9) (mm)	900	1000
11	Wear Resistance	LD - 2.01 (cycles)		4600