



INTERIOR GRADE LAMINATE

TECHNICAL SPECIFICATION

Sr No	Properties	Unit	Requirement as per EN438:2005	Alfaica Conforms
1	Thickness	3 mm	(± 0.30 mm)	√
	Length / Width	2440 x 1220 mm	(± 10, - 0 mm)	√
2	Density	g / cm ³	>1.35	1.45
3	Dimensional stability	% Max – “L” % Max – “T”	0.3 (max) 0.6 (max)	√ √
4	Wear Resistance	Cycles (min)	350(min)	400
5	Resistance to dry heat @ 180°C	Grade	Not worse than 3	√
6	Boiling water Resistance(max)	Mass Increase % (max) Thickness Increase % (max)	<4% <4%	3% 3%
7	Resistance to water Vapour	Appearance	Not worse than 4	√
8	Resistance to Cigarette Burn	Grade	Not worse than 3	√
9	Resistance to Crazing @ 80° C in Oven	Appearance	Not worse than 4	√
10	Resistance to Staining	Appearance Group 1 & 2 Group 3	Not worse than 5 4	√ √