



# POST FORMABLE LAMINATE

## TECHNICAL SPECIFICATION

Sr No	Properties	Unit	Requirement as per EN438:2005	Alfaica Conforms
1	Thickness	0.7 mm	(± 0.10 mm)	√
2	Length / Width	2440 x 1220 mm 3050 x 1300 mm	(± 10, - 0 mm) (± 10, - 0 mm)	√ √
3	Appearance		Should be free from foreign particles	YES
4	Density	gm / cm <sup>3</sup>	1	1
5	Dimensional stability	% Max – “L” % Max – “T”	0.55 (max) 1.05 (max)	√ √
6	Surface Wear Resistance	Cycles (min)	LD - 2.01	Min 4600 Cycles
7	Resistance to dry heat @ 180°C	Grade	4	>4
8	Boiling water Resistance	Mass Increase % (max) Thickness Increase % (max)	10 11.8	8 9
9	Resistance to Steam	Grade	4	>4
10	Resistance to Cigarette Burn	Grade	3	>3
11	Impact Strength	NEMA LD3 (3.9) (mm)	900	1000